

Product Data

llocut 603

High performance neat cutting oil

Description

Castrol Ilocut™ 603 is a chlorine and heavy-metal free neat cutting oil.

Application

Castrol llocut 603 has been designed for broaching and gear hopping opperations of ferrous alloys.

This product contains active sulphur and is not compatible with yellow metals.

üü suggested core application ü possible application, please consult Castrol representative prior to use

| | Cast Iron | Low-medium alloyed steel | High alloyed steel / nickel-chromium alloys | Titanium alloys | Aluminium alloys | Yellow metals |
|-------------------------------------|-----------|--------------------------|---|-----------------|---------------------|---------------|
| Honing/ Superfinishing | | | | | | |
| Grinding | ü | ü | ü | | ü | |
| Drilling | ü | ü | ü | | ü | |
| Broaching/ Gear manufactoring | üü | üü | ü | | ü | |
| General machining | üü | üü | üü | | ü | |

Advantages

- Selected additive technology can lead to extremely high cutting efficiencies, increased tool life, improved surface finish and lower overall operating costs
- Chlorine and heavy metal free which may help you to fulfil aspects of legislative requirements and waste treatment requirements where applicable

Typical Characteristics

| Properties | Standard | Unit | Data | |
|------------------|--------------------------|----------------|--------------|--|
| Appearance | Visual | | Yellow-Amber | |
| Viscosity @ 40°C | DIN 51562 ASTM D 445 | mm²/s | 33 | |
| Density @ 15°C | DIN 51757 ASTM D 1298 | kg/l | 0.88 | |
| Flashpoint COC | ISO 2592 ASTM D 92 | °C | >179 | |
| Copper corrosion | ISO 2160 ASTM D 130 | 3 hr at 100 °C | 4b | |

Additional Information

| | ester | active sulphur | inactive sulphur | phosphorous | calcium | chlorine | zinc |
|-----------|-------|----------------|---------------------|-------------|---------|----------|------|
| Additives | ü | ü | ü | | | | |

Storage

To avoid product deterioration always keep the container/drum tightly sealed. Store the product in a cool, dry place away from direct sunlight. Prevent exposure to frost and avoid water ingress. For optimum product stability, it is preferable to store the product indoors between 5°C and 45 °C / 41°F and 113°F.

For more details, please refer the product safety data sheet.

Ilocut 603 03 Nov 2014

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

 $Castrol\ Industrial, Technology\ Centre\ ,\ Whitchurch\ Hill\ ,\ Pangbourne\ ,\ Reading\ ,\ RG8\ 7QR\ ,\ United\ Kingdom$

www.castrol.com/industrial